

weber.color poxy



Category	<i>Improved reaction resin adhesive and reaction resin grout</i>
Composition	<i>Reactive resin, Hardener Mineral fillers, Additives</i>
Performance	<i>Conforms to En12004:2001 class R2 (Improved reaction resin adhesive) Rg1 (Reaction resin grout)</i>
European Norms test methods for adhesive	<i>EN12003-7.2, EN12003-7.3, EN12003-7.4, EN1346, EN12004 class R2</i>
European Norms test methods for grout	<i>EN12808-1, EN12808-2, EN12808-3, EN12808-4, EN12808-5</i>
Working time or Pot life	<i>30 minutes</i>
Temperature resistance	<i>-40°C to + 100°C</i>
Compressive strength	<i>About 65 MPa</i>
Bond/flexural strength	<i>25 MPa</i>
Shear strength	<i>14 MPa</i>
Dynamic modulus of elasticity	<i>4200 MPa</i>
Adhesion on concrete	<i>In dry conditions- >3 MPa In Wet conditions- >3 MPa</i>
Tiles/Granites	<i>All types</i>
Exposure	<i>Interior walls & floors Exterior floors Exterior walls</i>
Tile adhesive / Tile grout	<i>It can be both tile adhesive and tile grout</i>