

weberep repair mortar GP

weberep repair mortar GP use for repair concrete facades, spalling, honeycombing and restructuring balconies, terraces, walls and cornices.

- 2 - 35 mm. thickness application.
- Good bonding strength.
- Suitable for pre-cast, cast insitu, masonry and plastering surface.



Product detail

weberep repair mortar GP is pre-mixed, non-shrink, fiber-reinforced, cementitious mortar. Suitable for concrete, precast, masonry and plastering substrate. Can use to repair concrete facades, spalling, honeycombing and restructuring balconies, terraces, walls, cornices with 2-35 mm. thickness.

Consumption

Approximate 2 kg. of powder per 1 liter of mortar or 16 kg./m² at 10 mm. thickness.

Packaging

Bucket 5 kg.

Color

Grey (natural cement)

weberep repair mortar GP**Surface preparation**

- The surface must be free from oil, grease, paint and dust.
- The rebars should be free from rust, oil and grease.
- Remove all loose, unsound, contaminated concrete or laitance from the patch area.
- Brush, scrape or sandblast corroded rebars in order to remove non-adherent rust.
- Dampen the substrates with clean water to reduce water absorption.

Application

- Put the right proportion of clean water in the mixed container.
- Mix approximately 19-20% of water (0.95-1 liter) with 1 bucket (5 kg.) of **weberep repair mortar GP** or **weberep repair mortar GP** : water = 3.7 : 1 by volume
- Mix at the same time by using slow speed (<500 rpm) electrical mixer or hand-mixed by trowel in case of a little use.
- Leave the mortar at least 3-5 minutes.
- Apply by a trowel in 1 or 2 coats, pressing firmly to ensure bonding.
- When apply at the corner, use 2 trowel or install one side of formwork to prevent the mortar leak.
- Intervals between coats should be 2 to 3 hours.



weberep repair mortar GP

Uses and advantages

- Repair of chipped column, beam and floor.
- Repair of spalling and honeycombing on concrete surface.
- Repair footpath area.

Recommendations

- Do not add any admixtures or other materials.
- Do not add more water when the mortar is setting and should use within 2-3 hours.
- After finishing, protect the mortar from drying out by using the relevant curing method at least 3-7 days.

Shelf life and storage:

One year after manufacturing date when stored unopened in dry and ventilated place (store airtight in dry and ventilated conditions, if remained in opened bucket).

weberep repair mortar GP

Technical Data

Properties	weberep repair mortar GP
Density	1.35 kg./liter
Chemical curing time	3-5 mins
Pot life	2 hours
Application temperature	5-35 degree Celsius

Standard Test

Properties	weberep repair mortar GP
Compressive strength ASTM C109	>240 Ksc
Flexural Strength ASTM C348	6 N/mm ²
Setting time EN 195-3	
Initial setting time	2 hours
Final setting time	3 hours

