



webercolor slim

Special tile grout for very narrow joint 0.2 – 3 mm with anti-fungus property



For joint width between 0.2-3 mm.



For granito tiles, marble and granites



Flowable giving good adhesion with the grouted joints



Green label



Low porosity: anti-dirt



Low VOCs



Anti black mold and fungus



LEED

COLOR : 7 colors

SL-211	white	SL-214	light grey	SL-215	dark grey	SL-216	black
SL-221	cream	SL-252	light brown	SL-255	drak brown		

*These color presentations are as close as printing techniques permit. It is recommended to use the actual grout presenter for final selection.

webercolor slim is special tile grout for very narrow joint width with anti-fungus and anti-dirt properties giving good bonding ideal for grouting floors and walls of large size tiles, granito tiles, marbles, and granites

APPLICATION

Substrate preparation

- Properly clean the joints until free from any dirt to make sure of good bonding and color uniformity

Mixing

- Put clean water in mixing bucket
- Gradually add **webercolor slim** into the water with the ratio of 1 : 2.5 by volume (1 part of water + 2.5 part of the grout) and mix until obting homogeneous lump-free paste
- Leave the mixture for 3 – 4 minutes for chemical curing
- The mixture of **webercolor slim** can be used within 30 minutes after mixing when placing in shade

Grouting

- Use rubber trowel or grout trowel to diagonally fill up the joints.
- Wipe off excess grout with damp sponge before the grout sets.
- Leave for 2 hours and then clean tiles' surface with clean cloth
- Wait for 24 hours before traffic to ensure good bonding of the grout

SHELF LIFE AND STORAGE

18 months after manufacturing date when stored unopened in dry and ventilated place. Store airtight in dry and ventilated conditions if remained in opened bag



PACKAGING : 1 kg bag

COVERAGE : average 19 m² / 1 kg bag

TECHNICAL DATA	
Type	Cementitious grout
Density of powder	0.85 – 0.95 g/cm ³
Chemical curing time	3 – 4 minutes
Pot life (in shade)	30 minutes
Waiting time after tiling before grouting	24 hours
Recommended joint width	0.2 – 3 mm
Time before traffic	24 hours

Remark: These test results are from laboratory test. They could be slightly different from on-site results because of the differences in applications and conditions

CERTIFIED STANDARD		
International/European standard	Standard	Result
Flexural strength under standard condition ISO 13007 part 4-4.1.3 or EN 12808-3	≥ 2.5 N/mm ²	4.80 N/mm ² (48.92 ksc)
Compressive strength under standard condition ISO 13007 part 4-4.1.4 or EN 12808-3	≥ 15.0 N/mm ²	20.33 N/mm ² (207.26 ksc)
Shrinkage ISO 13007 part 4-4.3 or EN 12808-4	≤ 3 mm/m	2.52 mm/m
Water absorption after 30 minutes ISO 13007 part 4-4.2 or EN 12808-5	≤ 5 g	0.97 g
Water absorption after 240 minutes ISO 13007 part 4-4.2 or EN 12808-5	≤ 10 g	1.45 g
American standard/ANSI A118.6 (Unsanded)	Standard	Result
Linear Shrinkage	< 0.30 %	0.21 %
Water Absorption	< 18 %	12 %
Compressive Strength	1 day 28 day	> 500 psi > 3000 psi 1,986 psi 4,322 psi
Tensile Strength	28 day	> 250 psi 515 psi
Flexural Strength	28 day	> 500 psi 1,188 psi



**FACULTY OF ENGINEERING
CHULALONGKORN UNIVERSITY**

Type of test Compressive Strength (EN12808-3)

Test specimen Five (3) specimens in cube shape were cast in the laboratory.
The mix proportion of water to “Cementitious gouts (Weber. Color Slim)” ratio was 33% by weight.

Client Saint-Gobain Weber Co., Ltd.


Date of Test July 15, 2014

Test of method After mixing them thoroughly, the specimen were cast to the standard molds having a size of 40x40x40 mm. The specimens are cured for 24 hours in molds, then, stripped and cured in the room temperature until conducting the test.


Test Results The compressive strength of specimens at the age of 28 days are shown as follows.

Specimen No.	Width of Sample W (cm)	Length of Sample L (cm)	Thickness of Sample H (cm)	Maximum Load P (kgf)	Compressive Strength P/(WL) (kgf/cm ²)	Remarks (Specimen weight in gram, g)
1	4.00	4.00	4.02	3,350	209.38	99.06
2	4.00	4.01	4.03	3,600	224.44	100.42
3	3.99	4.00	4.01	3,000	187.97	96.17
				Average	207.26	

Note: These results certify the adequacy and representative character of test sample only.



 (Assoc. Prof. Dr. Tirawat Boonyatee)

Tested by : 

 (Assist. Prof. Dr. Boonchai Sangpetngam)

On Behalf of Head of Civil Engineering Department



**FACULTY OF ENGINEERING
CHULALONGKORN UNIVERSITY**

Type of test Flexural Strength (EN12808-3)

Test specimen Five (3) specimens in cube shape were cast in the laboratory.
The mix proportion of water to "Cementitious gouts (Weber. Color Slim)" ratio was 33% by weight.

Client Saint-Gobain Weber Co., Ltd.


Date of Test July 15, 2014

Test of method After mixing them thoroughly, the specimen were cast to the standard molds having a size of 40x40x160 mm. The specimens are cured for 24 hours in molds, then, stripped and cured in the room temperature until conducting the test.


Test Results The compressive strength of specimens at the age of 28 days are shown as follows.

Specimen No.	Width of Sample b (cm)	Length of Sample l (cm)	Thickness of Sample h (cm)	Maximum Load P (kgf)	Flexural Strength Sf (kgf/cm ²)	Remarks Sf=3PL/2bh ² , L=10 cm.
1	4.00	16.05	4.08	246	55.42	
2	4.00	16.04	4.04	214	49.17	
3	3.99	16.09	4.05	184	42.17	
				Average	48.92	

Note: These results certify the adequacy and representative character of test sample only.



 (Assoc. Prof. Dr. Tirawat Boonyatee)

Tested by : 

 (Assist. Prof. Dr. Boonchai Sangpetngam)

On Behalf of Head of Civil Engineering Department



**FACULTY OF ENGINEERING
CHULALONGKORN UNIVERSITY
MATERIAL TESTING LABORATORY**

Type of test	Water absorption of cementitious grouts after 30 and 240 min (EN12808-5)
Client	Saint-Gobain Weber Co., Ltd.
Test product	Tile Grout (Weber. Color Slim) – cementitious tile grout, provided by the client
Type of grout	Cementitious grout
Test procedure	Each specimen was weighed 28 days after mixing. Weight increment of each specimen was measured 30 min and 240 min after placing them vertically with the 40-mm x 40-mm end face submerged in 5 mm deep water.
Date of Test	July 15, 2014
Test conditions	Temperature =30°C , Relative humidity =66%

Test Results

(The test results are good only for the specimens tested.)

Specimen No.	Weight of Dry Specimen, g	Weight of Specimen, g		Water Absorption, g	
		After 30-min immersion	After 240-min immersion	After 30-min immersion	After 240-min immersion
1	396.20	396.90	397.65	0.70	1.45
2	401.70	402.60	402.80	0.90	1.11
3	384.70	386.00	386.50	1.30	1.80
Average=				0.97	1.45



 (Assoc. Prof. Dr. Tirawat Boonyatee)

Tested by : 

 (Assist. Prof. Dr. Boonchai Sangpetngam)

On Behalf of Head of Civil Engineering Department

CHULALONGKORN UNIVERSITY Department of Civil Engineering, Faculty of Engineering

Phayathai Road, Pathumwan, Bangkok 10330 Tel : (662) 218-6567 Fax : (662) 218-6567



**FACULTY OF ENGINEERING
CHULALONGKORN UNIVERSITY**

Type of test : SHRINKAGE TEST (EN 12808-4)
 Test specimen : Three (3) specimens in prism shape were cast in the laboratory.
 The mix proportioning of water to "weber.color slim" ratio was 33% by weight.
 Client : SAINT-GOBAIN WEBER CO., LTD.
 Date of test : July 15, 2014
 Test results : The shrinkage of specimens at the age of 28 days are shown as follows.


(The test results are good only for those specimens tested.)

Specimen No.	Initial Length (mm)	Final Length (mm)	Drying shrinkage of specimen (mm/m)
1	151.90	148.50	2.13
2	149.00	146.00	2.44
3	150.50	145.70	3.00

Note: This results certify the adequacy and representative character of the test samples only.


 (Assoc. Prof. Dr. Tirawat Boonyatee)

On Behalf of Head of Civil Engineering Department

Tested by : 
 (Assist. Prof. Dr. Boonchai Sangpetngam)

CHULALONGKORN UNIVERSITY Department of Civil Engineering, Faculty of Engineering
 Phayathai Road, Pathumwan, Bangkok 10330 Tel : (662) 218-6567 Fax : (662) 218-6567

TCNA TEST REPORT NUMBER: TCNA-0817-18 **PAGE:** 1 OF 3

TEST REQUESTED BY: Saint-Gobain Weber Co, Ltd.

TEST METHOD: ANSI A118.6 Specification for Standard Cement Grouts for Tile Installation

This specification describes the test methods and minimum requirements for standard cementitious grouts. Grouts meeting this specification may or may not contain polymers.

TEST SUBJECT MATERIAL: Identified by client as: “Webercolor Slim”

TEST DATE: 3/6/2018 – 4/3/2018

TEST PROCEDURE NOTES:

- Sample prep: The grout was mixed at a liquid to powder ratio of 30:100 parts by weight per the client’s instruction
- All samples were set up and cured according to ANSI A118.6.

TEST RESULTS:

Test Designation	Test Description	Evaluation	ANSI A118.6 Specification	
			Sanded	Unsanded
4.3	Linear Shrinkage Shrinkage based on initial bar length	0.21%	< 0.20%	< 0.30%
	Shrinkage based on 1 day specimen length*	0.12%		
4.4	Water Absorption 50% R.H. to Immersion	12%*	< 10%	< 18%
4.5	Compressive Strength 1-Day	1986 psi*	500 psi min.	500 psi min.
	28-day	4322 psi*	3000 psi min.	3000 psi min.
4.6	Tensile Strength 28-Day	515 psi*	300 psi min.	250 psi min.
4.7	Flexural Strength 28-day	1188 psi*	500 psi min.	500 psi min.

***COMMENTS:** The client requested that the shrinkage based on both the length of the initial bar length and based on the 1 day specimen length be reported. The results for water absorption, compressive strength, tensile strength, and flexural strength were first reported as part of TCNA-0215-18. The TCNA-0215-18 testing was performed on a different shipment of the material.



This report is confidential and has been prepared for the exclusive use of the client. It is not an endorsement, approval, certification, or criticism of any product by TCNA. This report shall not be published in any form without prior written consent from TCNA